

Primers & Overcoats

PRIMERS COMPARISON SHEET

October 1, 2015

We continuously work hard to improve our PermaBase and PermaFix range of primers and overcoats. We are proud to announce that for plastics and metals you now need only one primer product that gives unprecedented scratch resistance and much improved wash resistance

Please follow our instructions carefully in order to achieve best results. Remember, no two substrates are the same so a little bit of experimentation is critical before committing to a primer/substrate combination.

Substrate	Scratch Resistance	Cold Wash	Hot Wash	Comments
Glass PermaBase v1.0	● ● ●	●	●	5 min drying time
PermaFix v2.0	● ● ●	● ● ●	<60 deg C	24 hr drying time
Ceramics PermaBase v1.0	● ●	● ●	<35 deg C	5 min drying time
PermaFix v1.0	● ● ●	● ● ●	Boiling Point	24 hr drying time
Plastics PermaBase v2.0	● ● ●	● ● ●	●	No fix required
Metals PermaBase v2.0	● ● ●	● ● ●	<60 deg C	No fix required

- Suitable, 3 dots being the best
- Not suitable

Notes:

1. All goods are HAZMAT certified.
2. Minimum purchase quantity is 500ml.

Please note that all Primers and Overcoats are hazardous and the necessary protection standards need to be observed during their application.

Please allow all products to dry for 24 hours prior to washing them. Kindly observe washing temperatures